

TDS 0509

REVIEW: 01/2015

Standards: PETROBRÁS N-1850 B

Revran PFZ 520

Component A: 520.0485

Component B: 825.0720



Revran PFZ 520 uses specially selected raw materials, showing a high performance system. Product pigmented with anticorrosive - Zinc phosphate, it presents quick-drying and can be handled in a short time with long maximum recoating interval.

TECHNICAL CHARACTERISTICS**TYPE**

Polyamide-cured epoxy primer, two pack system.

USAGE

Recommended as coating of carbon steel structures, industrial equipments in general, marine, offshore in general, freeboard vessels and confined areas.

TECHNICAL INFORMATION

COLOR	Red Oxide	Other colors, please consult.	
FINISH	Matt		
VOLUME SOLIDS	47% ± 2	According to ISO 3233	
WEIGHT PER LITER	1,500 ± 0,05 g/ml	According to ASTM D 1475	
FLASH POINT	32°C		
MIXING RATIO		Weight	Volume
	Comp. A	100,0	4,0
	Comp. B	15,0	1,0
POT LIFE (25°C)	6 h		
INDUCTION TIME	15 to 30 min		
THEORETICAL SPREADING RATE	13,4 m ² /l - 35 µm		
WET THICKNESS	74 µm		
DRY THICKNESS	35 µm		
DRYING TIME, for 35 µm		25°C	

		Minimum	Maximum
	Touch		1 h
	Handle		4 h
	Recoat	12 h	6 months
ENVIRONMENTAL CONDITIONS	Temperature	Should be between 5 to 52°C	
	Relative Humidity	Between 30 to 85%	
	Dew Point	Surface temperature is at least 3°C above dew point	
	Thinner	420.0000	

APPLICATION	Brush	It is not necessary dilution. This method must be used only for retouch and backing of welding cords and corners.
	Roller	Dilute up to 10% (vol.) with recommended thinner. Must be used solvent resistant roller (sheep wool). The wool must be cutted (small size) to avoid blistering during the application.
	Conventional Spray Gun	Dilute up to 10% (vol.) with recommended thinner. Conventional DeVilbiss JGA 502 FX 704 spray gun or similar. Spray pressure between 2,5 to 3,0 kgf/cm ² (35 to 43 psi). Tank pressure between 0,5 to 1,5 kgf/cm ² (7 to 21 psi).
	AirLess Spray Gun	Dilute up to 10% (vol.) with recommended thinner. Use nozzles between 19 to 25 and pump pressure between 140 to 175 kgf/cm ² (2000 to 2500 psi).



SURFACE PREPARATION	Direct over carbon steel	Blast cleaning ISO 8501-1 Sa 2 ½ recommended. The surface must be dry, free of contaminants such as salt deposits, oil, grease, fat, dust and other kind of contaminants.
	Coated Surfaces	The surface must be clean and free of contaminants as oils, fat, grease and dust. Must not present peeling's areas. Proceed light sanding (220) to break the gloss.
	Recommended Primers	Not applicable
	Recommended TopCoat	Not applicable

SHELF LIFE 12 months

UN NUMBER 1263

HAZARD NUMBER 33

IMPORTANT RECOMMENDATIONS

1. The practical spreading rate of the product varies according to the applied thickness, application method and techniques, type and rugosity of the surface and ambient conditions.
2. The weight/l, viscosity and drying values were obtained in laboratory at a temperature of 25°C. At an altered temperature, the results might be different from the specified ones.
3. Low temperatures increase the curing time. At temperatures below 10°C, please contact our technical department.
4. Pot life is shortened by higher temperature and by the increase of catalyzed volume.

SAFETY PRECAUTIONS

1. Improper use and handling of this product can be hazardous to health and cause fire or explosion. Do not use it without first taking all appropriate measures to prevent property damage and injuries.
2. Storage: keep the product in sheltered, well-ventilated areas. Maximum temperature: 40°C. Must not be directly exposed to the sun.
3. Flammable: flammable product, which must be kept distant from ignition sources, and do not smoke nearby.
4. Inhalation: Avoid breathing vapors, keeping proper ventilation during application and drying.
5. Handling: wear proper protective clothing and masks, goggles, etc. Do not eat or drink nor allow children and animals to be near the application area.



HEALTH HAZARDS

1. Skin contact: wash affected area thoroughly with neutral soap.
2. Clothing contact: remove clothing and wash it.
3. Leakage: Isolate the area, and do not smoke nearby. If large quantity leaked in confined area, wear protective masks. Do not inhale vapors. Stop leakage with sand, sawdust or soil, and transfer liquid and solid to separated recipients for disposal.
4. Fire: protect non-affected recipients with water spray. Extinguish fire using carbon dioxide, foam or dry chemical.
5. Eyes contact: flush eyes with large amounts of clean water for at least 10 minutes, and get medical attention immediately.

IMPORTANT: For further information consult the product MSDS (Material Safety Data Sheet).
